

1641 Sigman Road  
PO Box 919  
Conyers, GA 30012  
1-770-922-8000 ext 164  
www.biomassenergylab.com



## Report of Analysis

McHale & Associates Inc.  
18378 Redmond Way  
Redmond WA 98052

Company Contact: James Hollibaugh  
[james.hollibaugh@mchale.org](mailto:james.hollibaugh@mchale.org)

<b>BEL ID Number(s):</b>	BEL123912	<b>Sample Weight (kg):</b>	7.32
<b>Product/Commodity:</b>	Woody Biomass	<b>Sample Received:</b>	11/24/2013
<b>Sample Designation:</b>	Test 1- Start 10:00	<b>Report Date:</b>	12/3/2013
<b>Packaging:</b>	Plastic Bag	<b>Report ID:</b>	BEL123912-1
<b>Date Sampled:</b>	11/21/2013	<b>Purchase Order #</b>	N/A

### Compositional Analysis: Proximate/Ulimate Analysis

Parameter	As-Received	Oven Dry	Analytical Method
Total Moisture (%)	37.62		CEN/EN 14774-1
Ash (%) - 815 C	3.04	4.87	CEN/EN 14775
Volatiles (%)			CEN/EN 15148
Fixed Carbon (%)			By Difference
Gross Calorific Value (MJ/kg)	12.05	19.32	CEN/EN 14918
Net Calorific Value (cV)(MJ/kg)	10.46	18.15	CEN/EN 14918
Net Calorific Value (cP)(MJ/kg)	10.36	18.09	CEN/EN 14918
Carbon (%)	30.39	48.72	CEN/EN 15104
Hydrogen (%)	3.53	5.66	CEN/EN 15104
Nitrogen (%)	0.24	0.39	CEN/EN 15104
Sulfur (%)	0.01	0.01	CEN/EN 15289
Oxygen (%)	25.17	40.35	By Difference

Prepared By: Chris Wiberg

Results shown on this certificate represent only the quantity of sample which was submitted for analysis. BEL does not assume responsibility for selection, representation, and/or sample identifications. Analyses are carried out within the scope of Principal's instructions and with due care and skill in conformity with BEL Terms and Conditions of Business. Claims in respect of services provided will be considered only if based upon failure to take due care proven by the Principal. Liability shall in no circumstances whatsoever exceed a total aggregate sum equal to 10 (ten) times the amount of the fee paid for the service.

1641 Sigman Road  
 PO Box 919  
 Conyers, GA 30012  
 1-770-922-8000 ext 164  
 www.biomassenergylab.com



## Report of Analysis

McHale & Associates Inc.  
 18378 Redmond Way  
 Redmond WA 98052

Company Contact: James Hollibaugh

<b>BEL ID Number:</b>	BEL123912	<b>Sample Weight (kg):</b>	7.32
<b>Product/Commodity:</b>	Woody Biomass	<b>Sample Received:</b>	11/24/2013
<b>Sample Designation:</b>	Test 1- Start 10:00	<b>Report Date:</b>	12/3/2013
<b>Packaging:</b>	Plastic Bag	<b>Report ID:</b>	BEL123912-1
<b>Seal Code:</b>	11/21/2013	<b>Purchase Order #</b>	N/A

### Major and Minor Elements:

Analyte	Dry Basis	Units	CEN/EN 15297
Aluminum (Al)	153.0	mg/kg	
Calcium (Ca)	6130	mg/kg	
Chromium (Cr)	<5.0	mg/kg	
Iron (Fe)	104	mg/kg	
Lead (Pb)	0.43	mg/kg	
Magnesium (Mg)	588.3	mg/kg	
Manganese (Mn)	71.3	mg/kg	
Mercury (Hg)	<0.020	mg/kg	
Phosphorus (P)	479	mg/kg	
Potassium (K)	1691	mg/kg	
Silica (Si)	6936	mg/kg	
Sodium (Na)	120	mg/kg	
Titanium (Ti)	7.8	mg/kg	

### Analysis of Ash: Ash Fusion Temperatures/Mineral Ash Analysis

Ash Fusion Property	Oxidizing (°C)	ISO 540
Shrinkage Starting Temperature (SST)	1230	
Deformation Temperature (DT)	1240	
Hemispherical Temperature (HT)	1270	
Flow Temperature (FT)	1280	

Prepared By: Chris Wiberg

Results shown on this certificate represent only the quantity of sample which was submitted for analysis. BEL does not assume responsibility for selection, representation, and/or sample identifications. Analyses are carried out within the scope of Principal's instructions and with due care and skill in conformity with BEL Terms and Conditions of Business. Claims in respect of services provided will be considered only if based upon failure to take due care proven by the Principal. Liability shall in no circumstances whatsoever exceed a total aggregate sum equal to 10 (ten) times the amount of the fee paid for the service.