1641 Sigman Road PO Box 919 Conyers, GA 30012 1-770-922-8000 ext 164 www.biomassenergylab.com



Report of Analysis

McHale & Associates Inc. Company Contact: James Hollibaugh

18378 Redmond Way <u>james.hollibaugh@mchale.org</u>

Redmond WA 98052

BEL ID Number(s): BEL123930 Sample Weight (kg): 3.84/4.01 **Product/Commodity:** Sample Received: **Woody Biomass** 11/24/2013 **Sample Designation:** Time 17:00 **Report Date:** 12/3/2013 Packaging: Plastic Bag Report ID: BEL123930-1 11/21/2013 Purchase Order # **Date Sampled:** N/A

Compositional Analysis: Proximate/Ultimate Analysis

•				
Parameter	As-Received	Oven Dry	Analytical Method	
Total Moisture (%)	38.11		CEN/EN 14774-1	
Ash (%)	1.99	3.21	CEN/EN 14775	
Volatiles (%)			CEN/EN 15148	
Fixed Carbon (%)			By Difference	
Gross Calorific Value (GJ/Tonne)	12.23	19.76	CEN/EN 14918	
Net Calorific Value (cV)(GJ/Tonne)	10.61	18.56	CEN/EN 14918	
Net Calorific Value (cP)(GJ/Tonne)	10.51	18.49	CEN/EN 14918	
Carbon (%)	30.55	49.36	CEN/EN 15104	
Hydrogen (%)	3.60	5.81	CEN/EN 15104	
Nitrogen (%)	0.24	0.39	CEN/EN 15104	
Sulfur (%)	0.01	0.01	CEN/EN 15289	
Oxygen (%)	25.51	41.21	By Difference	

Prepared By:

Results shown on this certificate represent only the quantity of sample which was submitted for analysis. BEL does not assume responsibility for selection, representation, and/or sample identifications. Analyses are carried out within the scope of Principal's instructions and with due care and skill in conformity with BEL Terms and Conditions of Business. Claims in respect of services provided will be considered only if based upon failure to take due care proven by the Principal. Liability shall in no circumstances whatsoever exceed a total aggregate sum equal to 10 (ten) times the amount of the fee paid for the service.

Chis Wiberg

1641 Sigman Road PO Box 919 Conyers, GA 30012 1-770-922-8000 ext 164 www.biomassenergylab.com



Report of Analysis

McHale & Associates Inc. Company Contact: James Hollibaugh

18378 Redmond Way Redmond WA 98052

BEL ID Number: BEL123930 Sample Weight (kg): 3.84/4.01 **Product/Commodity:** Sample Received: **Woody Biomass** 11/24/2013 **Sample Designation:** Time 17:00 **Report Date:** 12/3/2013 Packaging: Report ID: BEL123930-1 Plastic Bag

Seal Code: 11/21/2013 Purchase Order # N/A

Major and Minor Elements:

Analyte	Dry Basis	Units	CEN/EN 15297
Aluminum (Al)	136.1	mg/kg	_
Calcium (Ca)	4880	mg/kg	
Chromium (Cr)	<5.0	mg/kg	
Iron (Fe)	82	mg/kg	
Lead (Pb)	0.31	mg/kg	
Magnesium (Mg)	541.9	mg/kg	
Manganese (Mn)	72.8	mg/kg	
Mercury (Hg)	<0.020	mg/kg	
Phosphorus (P)	481	mg/kg	
Potassium (K)	1568	mg/kg	
Silica (Si)	5139	mg/kg	
Sodium (Na)	<100	mg/kg	
Titanium (Ti)	5.2	mg/kg	

Analysis of Ash: Ash Fusion Temperatures/Mineral Ash Analysis

Ash Fusion Property	Oxidizing (°C)	ISO 540
Shrinkage Starting Temperature (SST)	1240	
Deformation Temperature (DT)	1250	
Hemispherical Temperature (HT)	1260	
Flow Temperature (FT)	1270	

Prepared By:

Results shown on this certificate represent only the quantity of sample which was submitted for analysis. BEL does not assume responsibility for selection, representation, and/or sample identifications. Analyses are carried out within the scope of Principal's instructions and with due care and skill in conformity with BEL Terms and Conditions of Business. Claims in respect of services provided will be considered only if based upon failure to take due care proven by the Principal. Liability shall in no circumstances whatsoever exceed a total aggregate sum equal to 10 (ten) times the amount of the fee paid for the service.

Chis Wiberg